

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
5 January 2006 (05.01.2006)

PCT

(10) International Publication Number
WO 2006/001583 A1(51) International Patent Classification⁷: C21D 9/46

POSCO, 1 Koedong-dong Nam-ku, Pohang Kyungsang-book-do, 790-300 (KR).

(21) International Application Number:

PCT/KR2005/000828

(74) Agent: C & S PATENT AND LAW OFFICE; C-2306 Daelim Acrotel 467-6 Dogok-dong Kangnam-gu, Seoul 135-971 (KR).

(22) International Filing Date: 22 March 2005 (22.03.2005)

(25) Filing Language:

Korean

(26) Publication Language:

English

(30) Priority Data:

10-2004-0020204 25 March 2004 (25.03.2004) KR

10-2004-0103610

9 December 2004 (09.12.2004) KR

(71) Applicant (for all designated States except US): POSCO [KR/KR]; 1 Koedong-dong Nam-ku, Pohang, Kyungsang-book-do 790-300 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HAN, Seong-Ho [KR/KR]; c/o POSCO, 1 Koedong-dong Nam-ku, Pohang Kyungsangbook-do, 790-300 (KR). KIM, Tae-Kyu [KR/KR]; c/o Gwangyang Works, 700 Geumho-dong Donggwangyang Chunlanam-do, 545-090 (KR). HAN, Sang-Ho [KR/KR]; c/o Gwangyang Works, 700 Geumho-dong Donggwangyang Chunlanam-do, 545-090 (KR). KO, San-Kyung [KR/KR]; c/o Gwangyang Works, 700 Donggwangyang Donggwangyang Chunlanam-do, 545-090 (KR). CHIN, Kwang-Geun [KR/KR]; c/o POSCO, 1 Koedong-dong Nam-ku, Pohang Kyungsang-book-do, 790-300 (KR). KANG, Hee-Jae [KR/KR]; c/o

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COLD ROLLED STEEL SHEET AND HOT DIPPED STEEL SHEET WITH SUPERIOR STRENGTH AND BAKE HARDENABILITY AND METHOD FOR MANUFACTURING THE STEEL SHEETS



(57) Abstract: Disclosed herein are a bake-hardenable high-strength cold-rolled steel sheet, a hot-dipped steel sheet thereof, and a method for manufacturing the same. The steel sheet comprises 0.0016 ~ 0.01 % of C; 0.1 % or less of Si; 0.2 ~ 1.5 % of Mn; 0.05 ~ 0.15 % of P; 0.01 % or less of S; 0.08 ~ 0.5 % of (soluble) Al; 0.0025 % or less of N; 0.003 ~ 0.1 % of Nb; 0.003 % or less of Ti; 0.01 ~ 0.4 % of Mo; 0.0005 ~ 0.005 % of B; and the balance of Fe and other unavoidable impurities, in terms of weight%. The steel sheet has fine AlN precipitates, and a grain size (ASTM No.) of 9 or more. The AlN precipitates have a grain size, which can suppress grain growth. The steel sheet has enhanced strength, bake hardenability, aging resistance, and secondary work embrittlement resistance.